



# CB6-224 (6V224Ah at 20hr)



CB (Electric Vehicle) series is specially designed for frequent deep cycle discharge. By using the specially designed active material and strong grids, the CB series battery offers reliable performance in high load situations and can deliver more than 300 cycles at 100% DOD. Suitable for mobility scooters, electric wheel chairs, golf buggies etc.


## Specification

Cells Per Unit	3
Voltage Per Unit	6
Capacity	205Ah@10hr-rate to 1.80V per cell @25°C 224Ah@20hr-rate to 1.75V per cell @25°C
Weight	Approx. 29.0 Kg/4.99( Tolerance ±2%)
Max. Discharge Current	2050A (5 sec)
Internal Resistance	Approx. 2.5 mΩ
Operating Temperature Range	Discharge: -20°C ~60 °C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float charging Voltage	6.8 to 6.9 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	61.5 A
Equalization and Cycle Service	7.3 to 7.4 VDC/unit Average at 25°C
Self Discharge	CB Valve Regulated Lead Acid (VRLA) batteries can be stored for more than 6 months at 25°C. Self-discharge ratio less than 3% per month at 25°C. Please charge batteries before using.
Terminal	Terminal F14(M8)
Container Material	A.B.S. UL94-HB, UL94-V0 Optional.



## Dimensions

Unit: mm Dimension: 260(L) × 180(W) × 247(H) × 252 (TH) (mm)/ 10.24(L) × 7.09(W) × 9.72(H) × 9.92(TH) (inch)



### Constant Current Discharge Characteristics: A (25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
4.80V	732.9	539.6	398.2	233.0	133.3	81.28	54.82	45.58	36.33	26.21	21.33	11.92
5.00V	711.7	513.4	390.0	229.0	130.6	80.67	54.41	45.37	36.10	26.00	21.12	11.70
5.10V	690.6	495.3	383.9	224.8	127.3	80.06	53.38	45.16	35.87	25.79	20.91	11.47
5.25V	620.1	457.1	365.5	223.1	124.6	79.45	52.13	44.74	35.42	25.57	20.71	11.25
5.40V	559.7	416.8	336.9	219.3	121.0	78.02	51.27	43.68	35.16	25.15	20.52	11.14
5.55V	477.9	372.5	302.2	205.3	116.6	74.56	50.39	41.57	34.27	24.08	20.28	10.68

### Constant Power Discharge Characteristics: W(25°C)

F.V/Time	5M IN	10M IN	15M IN	30M IN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
4.80V	3866	2902	2203	1334	769.9	482.4	326.0	271.7	217.6	156.5	128.0	71.51
5.00V	3790	2813	2168	1317	768.0	480.9	324.6	271.3	216.0	155.7	127.2	70.17
5.10V	3747	2739	2151	1306	762.1	477.9	319.6	270.7	215.3	154.7	126.0	68.84
5.25V	3411	2550	2085	1312	747.1	476.5	312.5	268.2	213.2	153.4	124.8	67.50
5.40V	3107	2351	1927	1291	725.9	469.3	308.7	262.1	211.0	150.9	123.6	66.81
5.55V	2729	2146	1769	1216	700.4	449.1	303.5	249.4	206.0	144.5	122.0	64.10


All mentioned values are average values (Tolerance ±2%).

# CB6-224


6V224Ah




## Life characteristics of cyclic use




## Storage characteristic



## Charge characteristic Curve for standby use



## Discharge characteristic Curve



## Capacity Factors With Different Temperature

Battery Type		-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	6V&12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	6V&12V	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

## Discharge C current V S. Discharge V oltag e

Final D ischarge Voltage V /cell	1.75V	1.70V	1.60V
Discharge Current (A)	(A) ≤ 0.2C	0.2C < (A) < 1.0C	(A) ≥ 1.0C

Charge the batteries at least once every six months, if they are stored at 25°C.

Charging Method:

Constant Voltage	-0.2Cx2h+2.4-2.45V/cellx24h, Max. C current 0.3C
Constant Current	-0.2Cx2h+0.1Cx12h
Fast	-0.2Cx2h+0.3Cx4h

Bolt	M5	M6	M8
Terminal	F3 F4 F13 F18 T25 T26	F8 F11 F12-1 F15	F5 F9 F10 F12 F14 F16
Torque	6-7N-m	8-10N-m	10-12N-m

## Maintenance & Cautions

### Cycle service

- ※ Avoid battery over discharge, especially battery series connection use.
- ※ Charged with recommend voltage, ensure battery can be full recharged.
- In general, recharge capacity should be 1.1-1.15 times discharge capacity.
- ※ Effect of temperature on cycle charge voltage:  $-4mV/Cell$ .
- ※ There are a number of factors that will affect the length of cyclic service.
- The most significant are depth of discharge, ambient temperature, discharge rate, and the manner in which the battery is recharged.
- Generally speaking, the most important factors is depth of discharge.